

Certificate of Analysis


Customer: BIOCLAD
Certificate Number: BL040/2016
Date of testing: 08.08.16

Tel: +44 (0) 333 240 8308
Fax: +44 (0) 2476 338081
info@biolabtests.com
www.biolabtests.com

Test Method: Determination of Antibacterial Activity using the ISO22196: 2011 method

Sample	Test Bacterium	Contact Time		Red ⁿ against Initial	
		0 Hrs	24 Hrs	Log ₁₀	%
BioFloor vinyl safety flooring	MRSA	7.57E+05	≤11.11	≥4.83	≥99.99%
	<i>E.coli</i>	3.80E+05	≤11.11	≥4.53	≥99.99%

The above data describe the differences in the population sizes of the test organisms following their contact with the surface of the samples detailed in this CoA relative to the initial (0 hours) size of the populations (Termed 'Reduction against Initial'). Contact of the bacteria with the test materials was for 24 hours at 35°C under a RH of >95% as specified by the ISO22196 method



Maria Galino
Microbiologist,
BioLabTests

